

Certificate of Analysis

Article Name: WID®-easy PCR Kit

Catalogue Number: OE00083

Batch Code: SOLA-0006

Disclaimer: For *in vitro* diagnostic use.

Expiry Date: 2026-11-30

This product has been subjected to quality control and was tested in completion according to the assigned methods. All required specifications are met and therefore, the product is released for use.

Test	Specification	Result
OE-018-03_Comparison of labeled end product	The correct label was used and attached properly.	Yes
OE-018-03_Liquid in the tube	All filled tubes contain liquid.	Yes
OE-018-03_Correct filling volume	The filled tubes contain the specified filling volume $\pm$ 50% of the overfill volume.	Yes
OE-018-03_Performance of Primer Mix A in Positive Control	Mean ZSCAN12 Ct-Values are in the range of 26.5 to 27.5.	in spec
OE-018-03_Performance of Primer Mix A in Reference Sample 1 (15 copies)	Mean ZSCAN12 Ct-Values are in the range of 33.5 to 35.4.	in spec
OE-018-03_Absence of template in Primer Mix A_NTC	No Ct-Values below 43 are detected.	in spec
OE-018-03_Performance of Primer Mix A in Standard 1	Mean ZSCAN12 Ct-Values are in the range of 21.2 to 22.2.	in spec
OE-018-03_Performance of Primer Mix A in Standard 2	Mean ZSCAN12 Ct-Values are in the range of 24.5 to 25.5.	in spec
OE-018-03_Performance of Primer Mix A in Standard 3	Mean ZSCAN12 Ct-Values are in the range of 27.8 to 28.9.	in spec
OE-018-03_Performance of Primer Mix A in Standard 4	Mean ZSCAN12 Ct-Values are in the range of to 31.2 to 32.2.	in spec
OE-018-03_Slope of Standard curve in Primer Mix A_ZSCAN12	Slope is in the range of -3.4 to -3.3.	in spec
OE-018-03_Comparison of labeled end product Primer Mix B	The correct label was used and attached properly.	Yes
OE-018-03_Liquid in the tube	All filled tubes contain liquid.	Yes
OE-018-03_Correct filling volume	The filled tubes contain the specified filling volume $\pm$ 50% of the overfill volume.	Yes

OE-018-03_Performance of Primer Mix B in Positive Control	Mean GYPC Ct-Values are in the range of 24.3 to 25.8. Mean COL2A1 Ct-Values are in the range of 27.3 to 28.8.	in spec
OE-018-03_Performance of Primer Mix B Reference Sample 1 (15 copies)	Mean GYPC Ct-Values are in the range of 31.4 to 33.4.	in spec
OE-018-03_Absence of template in Primer Mix B_NTC	No Ct-Values below 43 are detected.	in spec
OE-018-03_Performance of Primer Mix B in Standard 1	Mean GYPC Ct-Values are in the range of 18.9 to 20.4. Mean COL2A1 Ct-Values are in the range of 21.8 to 22.8.	in spec
OE-018-03_Performance of Primer Mix B in Standard 2	Mean GYPC Ct-Values are in the range of 22.1 to 23.6. Mean COL2A1 Ct-Values are in the range of 25.3 to 26.5.	in spec
OE-018-03_Performance of Primer Mix B in Standard 3	Mean GYPC Ct-Values are in the range of 25.4 to 26.9. Mean COL2A1 Ct-Values are in the range of 28.6 to 30.3.	in spec
OE-018-03_Performance of Primer Mix B in Standard 4	Mean GYPC Ct-Values are in the range of 28.9 to 30.4. Mean COL2A1 Ct-Values are in the range of 32.0 to 34.3.	in spec
OE-018-03_Slope of Standard curve in Primer Mix B_GYPC	Slope is in the range of -3.4 to -3,3.	in spec
OE-018-03_Slope of Standard curve in Primer Mix B_COL2A1	Slope is in the range of -3.9 to -3.4.	in spec

DETERMINATION OF RELEASE: PASS

Storage: This product shall be stored protected from light between -25°C and -15°C.

Release Date:

2025-06-17

Signed by: Martin Widschwendter
Date: 19.06.2025 15:54:16
 This document is digitally signed! This document bearing a qualified electronic signature has the same legal standing as a handwritten document in accordance with Article 25(2) of Regulation (EU) No. 910/2014 of 23 July 2014 ("eIDAS-V0") Validation: Information for checking the electronic signature can be found at: www.a-trust.at/gpf

Prof. Martin Widschwendter

Chief Scientific Officer

Dr. Peter Kayatz

Chief Executive Officer

	Unterzeichner	Peter Kayatz
	Datum/Zeit-UTC	2025-06-20T13:53:03+02:00
	Prüfinformation	Informationen zur Prüfung der elektronischen Signatur finden Sie unter: https://www.signaturpruefung.gv.at
Hinweis	Dieses mit einer qualifizierten elektronischen Signatur versehene Dokument hat gemäß Art. 25 Abs. 2 der Verordnung (EU) Nr. 910/2014 vom 23. Juli 2014 ("eIDAS-V0") die gleiche Rechtswirkung wie ein handschriftlich unterschriebenes Dokument.	